



Green Synthesis of Silver Nanoparticles from *Astragalus Lagopoides* L. Leaves

Ramazan Erenler^{1,a,*}, Esma Nur Geçer^{2,b}

¹Health Sciences Faculty, Iğdır University, 76000 Iğdır, Türkiye

²Department of Chemistry, Faculty of Arts and Sciences, Tokat Gaziosmanpaşa University, 60250 Tokat, Türkiye

*Corresponding author

ARTICLE INFO

Research Article

Received : 27/03/2022

Accepted : 27/05/2022

Keywords:

Astragalus lagopoides

Natural products

Spectroscopy

Crystal structure

Pharmaceutical applications

ABSTRACT

Natural products have gained great interest due to their broad spectrum of biological activities. In this study, silver nanoparticles (AgNPs) were synthesized using *Astragalus lagopoides* L. by green approach. The structure of AgNPs was elucidated by spectroscopic techniques. UV-Vis spectrum presented the maximum absorption of AgNPs at 419 nm. The crystal structure of AgNPs was assigned as face centered cubic by X-ray diffraction (XRD) pattern. Scanning electron microscope (SEM) established morphology of AgNPs with an average size of 36.4 nm. *A. lagopoides* included the bioactive compounds, So, AgNPs capped by these compounds could be valuable substances for food and pharmaceutical applications.

^a erenler@gmail.com

^b <https://orcid.org/0000-0002-0505-3190> | esmanurgecer@hotmail.com

^c <https://orcid.org/0000-0002-0095-079X>



This work is licensed under Creative Commons Attribution 4.0 International License

Introduction

Medicinal plants play a significant role in drug development due to their biological activities (Dede et al., 2019, Erenler et al., 2019, Genç et al., 2019, Yaman et al., 2021). The advances in chromatography and spectroscopy in 19th century enabled the isolation and identification of bioactive compounds in the plants. Hence, plants became the focus of science, and many scientific studies were carried out to find the bioactive compounds that could be used in medicines (Elmastas et al., 2018, Erenler et al., 2018, Guzel et al., 2017, Karan et al., 2018a, Karan et al 2018b, Newman & Cragg 2007, Yildiz et al., 2017).

Nanotechnology is developing as a significant discipline of science with its various applications such as in pharmaceuticals, textile agriculture, catalysis, sensors, mechanics, optics, electronics, biomedicine (Ali et al., 2020, Karan et al., 2022, Sahin Yaglioglu et al., 2022).

Recently there has been a great interest in green synthesis of nanoparticles from plants (Alomar et al., 2020). The capping and stabilizing the metal by bioactive compounds could enhance biocompatibility. Metal and metal oxide nanoparticles are believed as the highly

suitable materials owing to their distinctive physical properties such as significant surface area to volume ratio, controlled morphology, smaller size, and light absorption properties (Erenler & Dag 2022). These properties enable them to be used in many areas such as biosensor, optoelectronics, and biomedicine (Burlacu et al., 2019).

The physical and chemical techniques have been used mostly for synthesis of nanoparticles (Geetha et al., 2013). However, these techniques require high energy, toxic chemicals, and harsh reaction conditions. The main drawback of these techniques is that the biocompatibility of nanoparticles is compromised due to the use of toxic chemicals in the synthetic stage (de Souza et al., 2019). Plant-based green approach has many advantages such as one-pot synthesis, robustness, low cost, and environmental friendliness, as well as the use of natural compounds from plants as reducing agents (Genc 2021). Therefore, the synthesis of nanoparticles using green approach, particularly plant-based techniques, is an alternative to these conventional procedures (Genc et al., 2021).

Astragalus L. genus belonging to the Fabaceae family has nearly 3000 species distributed mainly North America, Europe and Asia (Podlech 2008). Some species of this genus have been used as a folk medicine to treat various diseases such as gastric ulcer, bronchitis, hypertension, diabetes, gynaecological ailments (Benchadi et al., 2013). *Astragalus* species include the significant bioactive compounds such as saponins, flavonoids (Li-Xian et al., 1986, Yahara et al., 2000).

Herein, AgNPs were synthesized by eco-friendly, cheap, easy, and scale up manner. The structure of AgNPs was elucidated by spectroscopic techniques.

Plant Material

A. lagopoides was collected from Van region and taxonomic identification was carried out after comparison with the sample deposited at the Herbarium (13747) by Prof.Dr. Fevzi Özgökçe, Yüzüncü Yıl University, Van, Turkey.

Green Synthesis of Silver Nanoparticles

A. lagopoides leaves (10 g) were washed, dried, and powdered then heated in deionized water (100 mL) at 45°C for 2 hours. After double filtration with ordinary filter paper and Whatman (Grade 1) filter paper, the extract solution was treated with the deionized water solution of silver nitrate (0.35 M, 100 mL) for 2 h at 65°C. After the centrifugation of mixture at 5000 rpm for 15 min, the desired product was formed washed, and dried by lyophilisation (Erenler et al., 2021)

Characterisation of Nanostructures

The synthesized AgNPs were characterised by spectroscopic techniques. UV-Vis (UV-2600) spectrophotometer was used to reveal the maximum absorption of AgNPs. Empyrean, Malvern Panalytical diffractometer was utilized for X-ray diffraction (XRD) analysis to determine the crystal structure of AgNPs. Quanta Feg450 was used for scanning electron microscope (SEM) analysis to reveal the morphology of AgNPs (Gecer et al., 2022).

Results and discussion

UV-Vis Analysis

A. lagopoides leaves were used for synthesis of silver nanoparticles. The colour change of reaction mixture proved the formation of AgNPs. The maximum absorption at 419 nm verified the structure (Figure 1A). The reduction of Ag^{+1} ions was occurred by the molecules in *A. lagopoides* leaves. The silver nanostructures were formed by the redox reaction of *A. lagopoides* leaves solution with silver nitrate solution (Alomar et al., 2020).

X-ray Diffraction

XRD pattern indicated the crystal structure of synthesized nanoparticles. The diffraction peaks at 38.14°, 44.29°, 64.48° and 77.34° correspond to facets 111, 200, 220 and 311 of the face centered cubic crystal structure, respectively (Beyene et al., 2017) (Figure 1C) (Aravinthan et al., 2015).




Figure 1. UV-Vis spectrum (A), extract solution (1) and AgNPs solution (2). SEM image (B). XRD spectrum (C). EDX spectrum (D).

Scanning Electron Microscope Analysis

SEM analysis displayed the morphology of nanoparticles (Figure 1B). Formation of nanoparticles was also confirmed by the energy disperse analysis (EDX). The strong peaks around 3 and 3.4 keV in EDX spectrum supported the structure of nanoparticles (Figure 1D). The average particle size was calculated as 36.4 nm (Bachheti et al., 2020).

Conclusion

The synthesis of AgNPs using *A. lagopoides* by cheap, eco-friendly, one-pot and scale-up method was achieved. The structure of the green synthesized silver nanoparticle was elucidated by extensive spectroscopic study such as UV-Vis, XRD, SEM, and EDX techniques. The spectroscopic study showed the formation of well-dispersed, spherical, nanoparticles with an average size of 36.4 nm. *A. lagopoides* contains significant bioactive compounds. Hence, nanoparticles capped and stabilized by the corresponding compounds could be a promising material for food and pharmaceutical industries.

References

- Ali M, Ahmed T, Wu W, Hossain A, Hafeez R. et al. 2020. Advancements in plant and microbe-based synthesis of metallic nanoparticles and their antimicrobial activity against plant pathogens. *Nanomaterials*. 10: 1146. doi: <https://doi.org/10.3390/nano10061146>.
- Alomar TS, AlMasoud N, Awad MA, El-Tohamy MF, Soliman DA. 2020. An eco-friendly plant-mediated synthesis of silver nanoparticles: Characterization, pharmaceutical and biomedical applications. *Mater. Chem. Phys.* 249: 123007. doi: <https://doi.org/10.1016/j.matchemphys.2020.123007>.
- Aravinthan A, Govarthan M, Selvam K, Praburaman L, Selvankumar T. et al. 2015. Sunroot mediated synthesis and characterization of silver nanoparticles and evaluation of its antibacterial and rat splenocyte cytotoxic effects. *Int. J. Nanomed.* 10: 1977. doi:
- Bachheti RK, Fikadu A, Bachheti A, Husen A. 2020. Biogenic fabrication of nanomaterials from flower-based chemical compounds, characterization and their various applications: A review. *Saudi J Biol Sci.* 27: 2551. doi: <https://doi.org/10.1016/j.sjbs.2020.05.012>.
- Benchadi W, Haba H, Lavaud C, Harakat D, Benkhaled M. 2013. Secondary Metabolites of *Astragalus cruciatus* Link. and Their Chemotaxonomic Significance. *Rec Nat Prod.* 7
- Beyene HD, Werkneh AA, Bezabh HK, Ambaye TG. 2017. Synthesis paradigm and applications of silver nanoparticles (AgNPs), a review. *Sust. Mat. Technol.* 13: 18-23. doi: <https://doi.org/10.1016/j.susmat.2017.08.001>.
- Burlacu E, Tanase C, Coman NA, Berta L. 2019. A review of bark-extract-mediated green synthesis of metallic nanoparticles and their applications. *Molecules*. 24: 4354. doi: <https://doi.org/10.3390/molecules24234354>.
- De Souza TAJ, Souza LRR, Franchi LP. 2019. Silver nanoparticles: An integrated view of green synthesis methods, transformation in the environment, and toxicity. *Ecotox Environ Safe.* 171: 691-700. doi: <https://doi.org/10.1016/j.ecoenv.2018.12.095>.
- Dede E, Genc N, Elmastas M, Aksit H, Erenler R. 2019. Chemical Constituents Isolated from *Rhododendron ungueri* with Antioxidant Profile. *Nat Prod J.* 9: 238-43. doi: <https://doi.org/10.2174/2210315508666181024114812>.
- Elmastas M, Celik SM, Genc N, Aksit H, Erenler R, Gulcin İ. 2018. Antioxidant activity of an anatolian herbal tea—*Origanum minutiflorum*: isolation and characterization of its secondary metabolites. *Int J Food Prop.* 21: 374-84. doi: <https://doi.org/10.1080/10942912.2017.1416399>.
- Erenler R, Dag B. 2022. Biosynthesis of silver nanoparticles using *Origanum majorana* L. and evaluation of their antioxidant activity. *Inorg Nano-Met Chem.* 52: 485-92. doi: <https://doi.org/10.1080/24701556.2021.1952263>.
- Erenler R, Geçer EN, Genç N, Yanar D. 2021. Antioxidant activity of silver nanoparticles synthesized from *Tagetes erecta* L. leaves. *Int J Chem Technol.* 5: 141-46. doi: <http://dx.doi.org/10.32571/ijct.1005275>.
- Erenler R, Nusret G, Elmastaş M, Eminağaoğlu Ö. 2019. Evaluation of antioxidant capacity with total phenolic content of *Galanthus krasnovii* (Amaryllidaceae). *Turk J Biodiv.* 2: 13-17.
- Erenler R, Telci İ, Elmastaş M, Akşit H, Gül F, et al. 2018. Quantification of flavonoids isolated from *Mentha spicata* in selected clones of Turkish mint landraces. *Turk J Chem.* 42: 1695-705. doi: <https://doi.org/10.3906/kim-1712-3>.
- Gecer EN, Erenler R, Temiz C, Genc N, Yildiz I. 2022. Green synthesis of silver nanoparticles from *Echinacea purpurea* (L.) Moench with antioxidant profile. *Particul. Sci. Technol.* 40: 50-57. doi: <https://doi.org/10.1080/02726351.2021.1904309>.
- Geetha K, Umadevi M, Sathe G, Erenler R. 2013. Spectroscopic investigations on the orientation of 1, 4-dibromonaphthalene on silver nanoparticles. *Spectrochim. Acta A Mol. Biomol. Spectrosc.* 116: 236-41. doi: <https://doi.org/10.1016/j.saa.2013.07.039>.
- Genc N. 2021. Biosynthesis of silver nanoparticles using *Origanum onites* extract and investigation of their antioxidant activity. *Particul. Sci. Technol.* 39: 562-68. doi: <https://doi.org/10.1080/02726351.2020.1786868>.
- Genc N, Yildiz I, Chaoui R, Erenler R, Temiz C, Elmastas M. 2021. Biosynthesis, characterization and antioxidant activity of oleuropein-mediated silver nanoparticles. *Inorg. Nano-Met. Chem.* 51: 411-19. doi: <https://doi.org/10.1080/24701556.2020.1792495>.
- Genç N, Yıldız İ, Karan T, Eminağaoğlu Ö, Erenler R. 2019. Antioxidant activity and total phenolic contents of *Galanthus woronowii* (Amaryllidaceae). *Turk J Biodiv.* 2: 1-5.
- Guzel A, Aksit H, Elmastas M, Erenler R. 2017. Bioassay-guided isolation and identification of antioxidant flavonoids from *Cyclotrichium organifolium* (Labill.) Manden. and Scheng. *Pharmacogn Mag.* 13: 316. doi: <https://doi.org/10.4103/0973-1296.204556>.
- Karan T, Erenler R, Bozer BM. 2022. Synthesis and characterization of silver nanoparticles using curcumin: cytotoxic, apoptotic, and necrotic effects on various cell lines. *Z. Naturforsch. C.* <https://doi.org/10.1515/znc-2021-0298>.
- Karan T, Simsek S, Yildiz I, Erenler R. 2018a. Chemical composition and insecticidal activity of *Origanum syriacum* L. essential oil against *Sitophilus oryzae* and *Rhyzopertha dominica*. *Int J Sec Metabol.* 5: 87-93. doi: <https://doi.org/10.21448/ijsm.404114>.
- Karan T, Yildiz I, Aydin A, Erenler R. 2018b. Inhibition of various cancer cells proliferation of bornyl acetate and essential oil from *Inula graveolens* (Linnaeus) Desf. *Rec Nat Prod.* 12: 273-83.
- Li-Xian C, Xlao-Bing H, Yu-Qun C. 1986. The structures of thirteen astrasieversianins from *Astragalus sieversianus*. *Phytochemistry.* 25: 2389-93. doi: [https://doi.org/10.1016/S0031-9422\(00\)81702-1](https://doi.org/10.1016/S0031-9422(00)81702-1).
- Newman DJ, Cragg GM. 2007. Natural products as sources of new drugs over the last 25 years. *J Nat Prod.* 70: 461-77. doi: <https://doi.org/10.1021/np068054v>.
- Podlech D. 2008. The genus *Astragalus* L. (Fabaceae) in Europe with exclusion of the former Soviet Union. *Feddes Repertorium.* 119: 310-87. doi: <https://doi.org/10.1002/fedr.200811171>.
- Sahin Yaglioglu A, Erenler R, Gecer EN, Genc N. 2022. Biosynthesis of Silver Nanoparticles Using *Astragalus flavescens* Leaf: Identification, Antioxidant Activity, and Catalytic Degradation of Methylene Blue. *J. Inorg. Organomet. Polym. Mater.* <https://doi.org/10.1007/s10904-022-02362-5>.
- Yahara S, Kohjyouma M, Kohoda H. 2000. Flavonoid glycosides and saponins from *Astragalus shikokianus*. *Phytochemistry.* 53: 469-71. doi: [https://doi.org/10.1016/S0031-9422\(99\)00512-9](https://doi.org/10.1016/S0031-9422(99)00512-9).

- Yaman C, Sari Y, Atmaca S, Eroglu Z, Kayir O. et al. 2021. Chemical Composition and Biological Effects of Essential Oils from Some Aromatic and Medicinal Plants. *Nat Prod J.* 11: 699-706. doi: <https://doi.org/10.2174/2210315510999200811154403>.
- Yildiz I, Sen O, Erenler R, Demirtas I, Behcet L. 2017. Bioactivity-guided isolation of flavonoids from *Cynanchum acutum* L. subsp. *sibiricum* (willd.) Rech. f. and investigation of their antiproliferative activity. *Nat Prod Res.* 31: 2629-33. doi: <https://doi.org/10.1080/14786419.2017.1289201>.